

洋金粉粒度分布表

商品名 (Grade)		見掛密度 (Apparent Density)	水面被覆力 (Water – Covering Power)	粒径 (Particle Diameter)			厚さ(μm) (Thickness)	フルイ粒度分布 (μm-%) (Screen Analysis)				
赤口 (Pale Gold)	青口 (Rich Gold)	(g/cm ³)	(cm ³ /g)	Max.	Average	Min.	Average	+106	+75	+63	+45	-45
E5 (旧名:No.25)	E7 (旧名:No.27)	1.1~1.5	min 1500	100	35	15	0.80	—	max 2	max 10	10~20	min 70
L5 (旧名:No.35)	L7 (旧名:No.37)	1.0~1.4	min 1700	90	30	15	0.70	—	max 1	max 3	max 10	min 90
L5極細 (旧名:No.45)	L7極細 (旧名:No.47)	1.0~1.4	min 1900	80	28	13	0.60	—	max 1	max 2	max 8	min 93
2L5 (旧名:No.45特製)	2L7 (旧名:No.47特製)	1.0~1.4	min 2100	70	25	10	0.50	—	tr	max 1	max 5	min 95
3L5 (旧名:No.150)	3L7 (旧名:No.100)	1.0~1.4	min 3000	60	20	5	0.40	—	—	tr	max 3	min 97
4L5	4L7	1.0~1.4	min 3500	50	15	5	0.35	—	—	0	tr	100
No.50	No.70	—		40	10	2	0.25	—	—	—	0	100
No.500	No.700	—		25	7	2	0.20	—	—	—	0	100
No.5000	No.7000	—		15	5	1	0.18	—	—	—	0	100
No.5550	No.7770	—		10	3	1	0.15	—	—	—	0	100

※表の値は代表値であり、保証地ではありません (Figures in the above table are the typical values but not the guaranteed values.)